


## Product Data Sheet



### Product

#### Description

#### Availability

#### Typical End uses

#### Printing Capability

#### Converting Capability

### Pearl Digital Board

A rigid media for ink jet printing  
Product Strengths include excellent surface; outstanding flatness, brilliant semi-lustre surface, excellent whiteness, instant dry.

Stock and indent makings.

Photography, Portrait, Posters, Graphic Art Reproduction.

Waterbased inkjet dye and pigment ink systems.

1 side printable ready to frame and mount.

## SPECIFICATION

	UNITS STD		
Caliper	UM ISO534	1300	+/-50 um
Grammage	GM1 ISO 536	1000	+/-5%
Rigidity	Taber Stiffness		
Gloss (BYK) 60o	% 17 +/- 5		
Colour	MLD UVO L 92.2 +/-0.5		
	a -0.4 +/- 0.3		
	b -2.4 +/- 0.5		
	delta b 10.8 +/- 0.8		
CIE whiteness	(D65/10o)	145	

### Quality and Environmental Information

- James Cropper Converting Ltd is certified under ISO9001/2008 Quality system
- This product is manufactured on a site that is certified to ISO14001

### Safety Information

- This product does not come under CoSHH or REACH regulation, nonetheless a Health and Safety document is available on request

#### Data Sheet credit.

All properties according to James Cropper Converting Ltd., measurements.  
Test Climate 23°C/50%RH (according to ISO187). Tolerance based upon 95% confidence limits.

In order to verify, reel/pallet average shall be based on 5 single measurements randomly sampled within pallet.

