

filmoplast R

► **Repair paper with heat-activated adhesive**

Product information

- 8.5 g/m² light, transparent, technical Japanese paper
- coated with heatactivated acrylic-acid ester copolymer
- the paper is free of lignin and hemicellulose, with a high percentage of alpha cellulose
- the adhesive contains no softeners, is ageing-resistant, colourless and does not yellow
- Magnesium carbonate in the adhesive neutralises acids that may arise and migrate into the adhesive layer when paper fibres in old papers degrade
- the adhesive provides good adhesion with high bending stiffness, even repeated bending will not loosen the seal
- the sealing temperature must be over 100°C
- filmoplast R is reversible
- the lamination can be removed in a water bath or with alcohol. Attention! If using alcohol, check the solvent-resistance of the paper first.



Fields of application: filmoplast R is the ideal product for maintenance of modern papers and newspapers, retaining the paper character of the original. Due to the low thickness of the material, filmoplast R is hardly visible. The ageing resistance of the material was certified by PTS (Papiertechnische Stiftung München, Heidenau PBA-No.: 21.495/3). Continuous embedding from the roll is possible with the HRP hot-sealing machines. Fragmented documents can be joined up on the worktable of these machines and embedded between two layers of filmoplast R to form complete documents again. In order to invisibly repair tears, small rolls of filmoplast R can be used and sealed with a heating iron

For orders, sample requests, questions or suggestions please contact:

Neschen AG | Hans-Neschen-Str. 1 | D-31675 Bückeberg

Phone: +49 (0) 57 22-20 70 | Fax: +49 (0) 57 22-20 71 59 | E-Mail: info@neschen.de | www.neschen.com

Details

26200	50m x 2cm	
26201	50m x 31cm	
26202	50m x 41cm	
26203	50m x 62cm	
6012831	50m x 93cm	
38514	200m x 31cm	
38687	200m x 41cm	
38078	200m x 62cm	

For orders, sample requests, questions or suggestions please contact:

Neschen AG | Hans-Neschen-Str. 1 | D-31675 Bückeberg

Phone: +49 (0) 57 22-20 70 | Fax: +49 (0) 57 22-20 71 59 | E-Mail: info@neschen.de | www.neschen.com